



TECHNICAL DATA SHEET

DESCRIPTION

B-5023 / A-2732 is a High Service Temperature polyurethane spray foam system specially formulated without any ozone depletion substances. This system is designed to withstand service temperature as high as 285°F (141°C). This system is formulated with renewable and recycled products.

REACTIVITY PROFILE

Cream Time

0-1 second

Gel Time

3-4 seconds

Rise Time

5-6 seconds

COMPONENT PRODUCT SPECIFICATIONS

PROPERTY	POLYMERIC ISOCYANATE A-2732	B-5023 RESIN
Appearance	Brown liquid	Amber liquid
Viscosity at 25°C	150-250 cps	200-400 cps
Specific gravity	1.22 – 1.25	1.15 – 1.20
Shelf life	12 months	6 months

TYPICAL PHYSICAL PROPERTIES

PHYSICAL PROPERTIES	STANDARD	RESULT
Density (Core)	ASTM D1622	36 kg/m ³ (2.25 lb/ft ³)
Compressive Strength	ASTM D1621	236 kPa (34.2 psi)
Dimensional Stability	ASTM D2126 (28 days, -20°C, Ambient R.H.)	-0.43%
	ASTM D2126 (28 days, +80°C, Ambient R.H.)	2.56%
	ASTM D2126 (28 days, +70°C, 97%+-3% R.H.)	4.78%
Water Absorption (volume)	ASTM D2842	<1.0%
Initial Thermal Resistance (50mm)	ASTM C518	7.12 ft ² .h. ⁰ F/btu.in (1.25 m ² .°C/W)

Genyk Inc believes that the information in this technical data sheet is an accurate description of the typical uses of the product. Genyk Inc, however, disclaims any liability for incidental or consequential damages, which may result from the use of the product that are beyond its control. Therefore, it is the user's responsibility to thoroughly test the product in their particular application to determine its performance, efficiency and safety. Nothing contained herein is to be considered as permission or a recommendation to infringe any patent or any other intellectual property right.